Case Study



Viscotaq Viscous Elastic Wrapping (Viscopaste, Viscowrap HT, PVC & PU composite wrap) on Soil to Air Riser



Viscotaq Viscous Elastic Wrapping (Viscopaste, Viscowrap HT, PVC & PU composite wrap) on Soil to Air Riser

Surface Preparation

Pineline suffered severe external corr

Pipeline suffered severe external corrosion. Surface preparation up to St2



2 Viscotaq® Viscowrap Application

Viscotaq® Viscowrap HT is applied by removing the release liner and placing adhesive side on the pipe. Initial wrap should be a straight circumference wrap. Once initial straight circumference wrap is completed, wrap with slight tension and a minimum 1/2" overlap.



3 Viscotaq® PVC Outerwrap Application
Outer Wrap should be wrapped with tension
and a minimum of 50 % overlap. First wrap
and termination wrap should be a straight

circumference wrap



Viscotaq Viscous Elastic Wrapping (Viscopaste, Viscowrap HT, PVC & PU composite wrap) on Soil to Air Riser

4 Viscotaq® PU Composite Wrap Application

As an additional mechanical protection, Viscotaq PU polyurethane layer with 66 % overlap over the PVC layer.



5 UV Resistant Top Coat

The final layer has to be painted with a UV Resistant Top Coat.



7 Design Criteria

Operating Pressure : 60 Bar

Temperature : Ambient

Defect Type : External corrosion

Size : 42"

Material : API 5L – X 60

Location : UAE